



CERAGLO – ACIDIC BASED RUST, WATER STAIN AND SCALE REMOVER

WHAT CERAGLO DOES

CERAGLO IS A FREE-FLOWING ACIDIC LIQUID CONCENTRATE INTENDED FOR DILUTION WITH HOT OR COLD WATER. IT IS SAFE AND PLEASANT TO USE AND AT THE SAME TIME HIGHLY EFFICIENT FOR THE REMOVAL OF RUST AND SCALE BY CHEMICAL ACTION. CERAGLO ALSO CONTAINS POWERFUL WETTING AGENTS AND SOLVENTS WHICH ENABLE IT TO LEACH DIRT WHICH HAS PENETRATED THE SURFACE BEING TREATED. THE PRODUCT HAS BEEN SPECIFICALLY FORMULATED SO THAT IT HAS NO UNPLEASANT SMELL, NOR WILL IT LEAVE ANY AFTER USE.

CERAGLO IS NOT A DEGREASER. IN ORDER TO MAXIMISE EFFICIENCY, OIL OR GREASE SHOULD BE REMOVED FROM THE SURFACE BEFORE APPLYING THE CERAGLO SOLUTION. ONE OF OUR EMULSIFIERS SUCH AS SOLCON 80R SHOULD BE USED FOR THIS PURPOSE.

RUST REMOVAL

THE SURFACE OR COMPONENTS TO BE TREATED SHOULD FIRST BE BRUSHED WITH A STIFF WIRE BRUSH TO REMOVE LOOSE RUST FLAKES OR SCALE. THIS ENSURES MORE ECONOMICAL USE OF THE CERAGLO.

AFTER THE ABOVE TREATMENT, APPLY A SOLUTION OF 1 PART CERAGLO TO 3 TO 6 PARTS WATER. APPLICATION MAY BE BY BRUSH, CLOTH OR SPRAY.

COMPONENTS MAY BE DIPPED IN THE SOLUTION, USING A PLASTIC, RUBBER-LINED OR STAINLESS STEEL CONTAINER. QUICKEST RESULTS WILL BE OBTAINED IF THE SOLUTION IS HOT. AS SOON AS THE SURFACE OR COMPONENTS ARE FREE OF RUST OR SCALE, REMOVE FROM THE CERAGLO SOLUTION AND RINSE PROMPTLY WITH WATER. FOR BEST RESULTS, BRUSH OR WIPE WHILE RINSING.

TO PREVENT FURTHER CORROSION, PARTS SHOULD BE TREATED WITH AN AGMAPEL OR SYNERGEN ANTI CORROSION COATING, OR PAINTED.

CLEANING AND BRIGHTENING STAINLESS STEEL

CERAGLO IS EXCELLENT FOR CLEANING AND BRIGHTENING STAINLESS STEEL TANKS AND EQUIPMENT. DILUTE WITH 4 TO 20 PARTS HOT WATER, DEPENDING UPON CONDITIONS. CERAGLO IN ANY STRENGTH HAS NO CORROSIVE EFFECT ON STAINLESS STEEL.

ALWAYS FINISH WITH A COLD WATER RINSE. DRY VERY THOROUGHLY.

RESTORATION OF GLAZED SURFACES, TOILETS, BATHS, BASINS, CONCRETE AND TERRAZZO

INGRAINED DIRT, CALCIUM AND MAGNESIUM DEPOSITS, EVEN RUST AND URIC ACID STAINS, CAN BE QUICKLY REMOVED.



FIRST CLEAN THE SURFACE TO REMOVE SUPERFICIAL DIRT AND GREASE. WET THE SURFACE THOROUGHLY BEFORE APPLYING THE CERAGLO SOLUTION.

WITH A MOP, BRUSH OR SPONGE, APPLY A SOLUTION OF 1 PART CERAGLO TO 20 PARTS HOT WATER AND ALLOW TO SOAK FOR AT LEAST 10 MINUTES. TO ENSURE BEST RESULTS, BRUSH THE SURFACE AT THE SAME TIME. DO NOT ALLOW THE CERAGLO SOLUTION TO DRY. IF THE SOLUTION TENDS TO DRY DURING THE SOAKING PERIOD, ADD EXTRA WATER.

FINALLY, HOSE AND RINSE THE SURFACE THOROUGHLY WITH COLD WATER.

RESTORATION OF WOODEN SURFACES

STAINS AND INGRAINED DIRT CAN BE EASILY REMOVED BY A SOLUTION OF 1 PART CERAGLO TO 10 PARTS WATER. APPLY WITH A BRUSH TO THE SURFACE, LEAVE 10 TO 15 MINUTES, THEN HOSE OR RINSE THOROUGHLY WITH COLD WATER. REPEAT TREATMENT UNTIL STAIN IS REMOVED AND WOOD IS RESTORED.

EQUIPMENT

USE STAINLESS STEEL, PLASTIC, CERAMIC OR RUBBER-LINED EQUIPMENT FOR HANDLING CERAGLO. DO NOT USE GALVANISED OR TINNED EQUIPMENT. RINSE ALL EQUIPMENT WITH WATER AFTER USE.

ROPES AND FABRICS

CERAGLO MUST NOT BE ALLOWED TO SPLASH ON TO ROPES AS THIS CAN CAUSE WEAKENING OF THE FIBRES. CLOTHING AND FABRIC WHICH HAS BEEN SPLASHED MUST BE RINSED PROMPTLY WITH WATER.

HEALTH AND SAFETY

SEE SEPARATE SAFETY DATA SHEET

THE INFORMATION CONTAINED IN THIS DATA SHEET IS ACCURATE TO THE BEST OF OUR KNOWLEDGE AND BELIEF. NO WARRANTY IS, HOWEVER, GIVEN OR IMPLIED. CONSULT AGMA LTD CONCERNING ALL NON-STANDARD APPLICATIONS.

ISSUE NO. 4-7/22